

**Doppelseitig silikonisierte transparente
PET-Folie 30 my-473**

Siliconized transparent PET-film 30 my-473
double side siliconized

Artikel / Article A322

VPF GmbH & Co. KG
Harkortstraße 14-16
45549 Sprockhövel (Germany)
Telefon +49 (0)2339 1205-0
Telefax +49 (0)2339 1205-50
info@vpf.de
www.vpf.de

| Eigenschaften Properties | Besonderheiten Special features | Typische Werte Typical values | Einheit Unit | Normen Prüfbedingungen Norms Test requirements |
|--|--|----------------------------------|--------------------|---|
| Dicke Caliper | | 30 ± 5% | µm | |
| Gewicht Specific Weight | | 1,40 | g/cm ³ | |
| Reißdehnung Elongation at break | längs/MD quer/CD | 60 - 150 60 - 150 | % | ASTM D 882 |
| Reißfestigkeit Tensile strength at break | längs/MD quer/CD | 19,0 ± 20% 19,0 ± 20% | Kg/mm ² | ASTM D 882 |
| Schrumpf (150°C-30 Min.) Shrink (150°C-30 min.) | längs/MD quer/CD | 0,6 – 2,5 0,0 - 1,5 | % | |
| Trennwert Release | | 25 ± 10% | g/in | Int. Method from FTM4 TESA TAPE 7475 |
| Restklebkraft Subsequent adhesion force | | > 80,0 | % | Int. Method from FTM11 TESA TAPE 7475 |
| Besonderheiten Special features | Die Eignung muss vom Anwender individuell getestet werden. We recommend trials and testings beforehand. | | | |

Alle Angaben informieren über unsere Produkte, sie gelten nicht als Zusicherung bestimmter Eigenschaften und stellen Durchschnittswerte und unsere gegenwärtigen Erfahrungswerte dar. Es obliegt dem Anwender selbst zu prüfen, ob sich das Produkt auch unter den anwendungsbezogenen Einflüssen für die vorgesehene Verwendung eignet. Eine Haftung für unsere Produkte übernehmen wir ausschließlich nach Maßgabe unserer allgemeinen Verkaufsbedingungen, soweit nichts Anderes vereinbart wird. Technische Änderungen behalten wir uns jederzeit vor. Stand: 10/2021 - Alle vorherigen Produktinformationen werden ungültig und durch diese Version ersetzt.

These recommendations are based on our actual knowledge and experience of the products stated, but should not in any way be considered to be "Warranted Characteristics". As the products are used outside our control we are unable to accept any responsibility for loss or damage, however caused, which may result from the use of these products. Unless otherwise agreed, any assumption of product liability will be strictly in accordance with our general Conditions of Sale. All technical information is subject to change without notice. Last update: 10/2021 - This product information is replacing and annulling all previous versions.